

TYPICAL PROPERTIES

- •Appearance and odor = Thick, green paste
- $\bullet pH = NA$
- •VOC (EPA 24) = Not determined
- •Density = 6.88 lbs/gal
- •Flashpoint = 126 °F

SHIPPING

FoundryGeneral® Sand Treatment 16-250 is shipped in metal drums and pails.

FoundryGeneral® Sand Treatment 16-250

Foundry Sand Additive

Description

FoundryGeneral® Sand Treatment 16-250 is used as a lubricant and release agent for Green Sand, Core Oil, Hot Box and Sodium Silicate sand mixes. FoundryGeneral® Sand Treatment 16-250 is a blend of solvent and waxes, which increases lubricity, reduces sticking and increases sand density. It out performs kerosene and other lubricating oils in reducing sticking; promotes core oil dispersion in a muller; increases sand flowability and reduces clean up of sand handling equipment.

Recommended Application

FoundryGeneral® Sand Treatment 16-250 is used as received.

It is added at a ratio of $\frac{1}{4}$ percent (based on sand weight) to the sand.

Mix sand for 15 seconds prior to discharge.

Benefits

- •Increases lubricity
- Reduces sticking
- •Reduces clean up

Material Compatibility

Product is combustible. Avoid heat, sparks and open flames. Avoid strong oxidizing agents (i.e. bleach) and strong acids.

Health & Safety

Please refer to SDS for complete health and safety information.

Storage

Please refer to SDS for storage information. Shelf life is 1 year from date of manufacture.

12336 Emerson Dr. | Brighton, MI 48116 | 248-587-5600 Fax: 248-587-5606 | www.gccdatasheets.com