

FoundryGeneral® Foundry Cleaner 2988

Solvent Based Immersion Cleaner

TYPICAL PROPERTIES

• Appearance and odor = Clear, colorless to pale yellow liquid • pH = NA • VOC (EPA 24) = 7.7 lbs/gal • Density = 8.5 lbs/gal • Flashpoint = 250 °F

SHIPPING

FoundryGeneral® Foundry Cleaner 2988 is shipped in 1 gallon plastic jugs, 5 gallon plastic buckets, or 55 gallon closed head plastic drums.

Description

FoundryGeneral® Foundry Cleaner 2988 is a unique water extended NMP formulation that has been designed to aggressively break down urethane resins and release agents from the screens, vents and surface of core boxes.

Recommended Application

1

FoundryGeneral® Foundry Cleaner 2988 is used as received. It has been formulated to be used in an immersion system. FoundryGeneral® Foundry Cleaner 2988 should be heated to a temperature between 100 to 150°F and agitated by some means (i.e. mixer, air, ultrasonic). The warmer the material, the more effective it will be. Boxes should remain immersed 15 to 20 minutes before removal at which point they should be blown off or steam cleaned. Please refer to the MSDS for proper safety instructions.

FoundryGeneral® Foundry Cleaner 2988 is used as received. It has been formulated to be used in an immersion system. FoundryGeneral® Foundry Cleaner 2988 should be heated to a temperature between 100 to 150°F and agitated by some means (i.e. mixer, air, ultrasonic). The warmer the material, the more effective it will be. Boxes should remain immersed 15 to 20 minutes before removal at which point they should be blown off or steam cleaned. Please refer to the MSDS for proper safety instructions.

Benefits

• Non corrosive • Non flammable • Reclaimable • Effective resin removal

Material Compatibility

Avoid heat, sparks and open flames. Avoid strong oxidizing agents (i.e. bleach) and strong acids.