

# DECONPEEL NUCLEAR

Peelable Coating/Temporary  
Maskant



## TYPICAL PROPERTIES

Color: Clear dry film  
Weight: 9.3 lbs/gallon  
Viscosity: 8,000-14,000  
centipoise  
Flashpoint: None

## SHIPPING

DeconPeel Nuclear is shipped in  
1 gallon metal cans, 5 gallon  
plastic buckets, or 55 gallon  
open head plastic drums.

## Description

Deconpeel Nuclear is a water based peelable Coating. It is VOC and halogen free. Deconpeel is a non-hazardous, non-toxic solution formulated for removing and preventing the spread of chemical contamination. Deconpeel is used for the decontamination of floors, walls and equipment. While curing, DeconPeel mechanically and chemically entraps contamination. After curing, the coating strips off, along with loose surface contamination. Deconpeel can also work as a shield or barrier to prevent contamination or as a covering to contain contamination.

## Recommended Application

- 1 Perform patch test.
- 2 Deconpeel should be used as received.
- 3 It is applied by airless spray, brushing or dipping.
- 4 Apply a minimum of 8 mils (.008) of wet film.
- 5 Allow coating to cure thoroughly before removal.

## Benefits

Multifunctional products.  
More effective protection.  
Easy application.  
Zero VOC

## Health & Safety

Please refer to SDS for complete health and safety information.

## Patch Test:

Because it is difficult to determine the type of substrate, perform a small test first. This will determine effectiveness, coverage, and the approximate amount of time required for it to work.

## Application

For best results should be applied at 45F to 100F and low humidity.

## Tack Free Drying time

· The sprayed coating dries to touch in 10 minutes or less, depending on  
· temperature and film thickness. Deconpeel will cure tack-free within 60  
· minutes after application. This is dependent upon temperature, humidity  
· and thickness of coating. Curing may be accelerated by forced drying. It  
· is imperative that Deconpeel be thoroughly cured and dry, with no water  
· being felt before an attempt is made to strip the coating from the  
· substrate.

### **Coverage**

· When applied to 8 mils thick, DeconPeel will provide approximately 200  
· square feet of coverage.

### **Removal**

· Coating is removed by peeling.

12336 Emerson Dr. | Brighton, MI 48116 | 248-587-5600  
Fax: 248-587-5606 | [www.gccdatsheets.com](http://www.gccdatsheets.com)