GENERAL CHEMICAL CORP.

TACKY BOOTH COATING-3228

TBC- 3228



TYPICAL PROPERTIES

• Appearance: Clear, viscous, odorless liquid
• pH = 6.0-7.0
• VOC (EPA 24) = 0.2-0.3 lbs/gal
• Flashpoint = None to boiling
• Specific Gravity: 1.0-1.1
• Viscosity: 45,000-70,000 cps

SHIPPING

Tacky Booth Coating 3228 is shipped in 1 gallon metal cans, 5 gallon plastic bucket, or 55 gallon closed head plastic drum.

Description

Tacky Booth Coating 3228 is a water based, soft, clear, temporary booth coating that provides an excellent barrier for both water based and solvent based paints. When used in automotive spray paint booths, Tacky Booth Coating 3228 prevents heavy accumulations of paint over-spray from adhering to walls, windows, center tracks, and robot covers, simplifying booth maintenance. The product remains soft, clear, and tacky so that it can be easily removed by scraping. And since it is water based, Tacky Booth Coating 3228 can be removed with a stream of water from a water hose.

Recommended Application

1. Tacky Booth Coating 3228 is used as received.
2. It can be brushed, rolled, or sprayed onto the surface to be coated.
3. Remove coating by scraping or water stream.

Benefits

• Water Based
• Soft, Scrapable Film
• Water Rinse-able
• Long Lasting Tack
• Easily Applied

Health & Safety

Please refer to SDS for complete health and safety information.

Storage

KEEP FROM FREEZING! Store in a dry location at room temperature. Keep container closed and maintain all original markings and labels.

Application

Airless spray is the preferred and recommended method due to the ease with which this is accomplished. The coating thickness depends upon the amount of paint overspray that will accumulate.

Removal

Tacky Booth Coating 3228 is then removed either by scraping it from the surface or by rinsing with a water hose.

12336 Emerson Dr. | Brighton, MI 48116 | 248-587-5600
Fax: 248-587-5606 | www.gccdatasheets.com