



### TYPICAL PROPERTIES

#### APPEARANCE AND ODOR:

Clear to milky thick paste, mild odor

BOILING POINT: >212°F

pH: 2.5-3.5

### SHIPPING

Stripoxy 8649 is shipped in 1 gallon plastic jugs, 5 gallon plastic buckets, or 55 gallon closed head plastic drums.

# STRIPOXY 8649

## PAINT STRIPPER

### Description

Stripoxy 8649 is a thickened paint remover formulated to undercut and strip cured powder coating from aluminum, steel and many non-ferrous substrates in 30 minutes to 2 hours at room temperatures.

### Recommended Application

- 1 Apply StripOxy 8649 generously by brush, roller or airless spray to surfaces to be stripped.
- 2 Let product stand for 30 to 120 minutes.
- 3 Once coating is softened and undercut, remove with scraper or warm pressure water rinse.

### Health & Safety

May be harmful if swallowed. May cause skin and eye irritation. Eye protection and rubber gloves are recommended when handling this product. Please refer to SDS for complete health and safety information.

### Storage

Store in sheltered area, away from temperature extremes in labeled containers. Keep away from freezing. Store in dry and ventilated area. Keep containers closed when not in use. Do not store with strong bases or oxidizing agents.

### Surfaces

For use on: aluminum, steel and many non-ferrous substrates.