



TYPICAL PROPERTIES

Color: clear

Weight: 8.87 lbs/gallon

Viscosity: 50-60 sec on Zahn 4 cup

Flashpoint: None

SHIPPING

Boothcoat 5140 is shipped in 1 gallon metal cans, 5 gallon plastic buckets, or 55 gallon open head plastic drums.

BOOTHCOAT 5140

Peelable Coating

Description

Boothcoat 5140 is a temporary, clear, peelable coating and can be used as a peelable coating on spray booth for protection on glass, plexiglass, rubber, cement, aluminum and many other hard surfaces. Boothcoat 5140 represents the ultimate in non-solvent peelable coatings. It is well stabilized against brittleness and it will not be softened or penetrated by most solvent-based paints. Boothcoat 5140 has no VOC's.

Recommended Application

1

Perform patch test.

2

Boothcoat 5140 should be used as received.

Airless sprayer is recommended application method.

3

Apply a minimum of 8 mils (.008) of wet film.

Benefits

Multifunctional product
More effective protection
Easy application

Health & Safety

Please refer to SDS for proper safety instructions.

Storage

Product has a shelf life of one year from date of manufacture.

Patch Test

Because it is difficult to determine the type and condition of the surface, perform a small patch test first. It will determine the peelability of the coating on your particular surface, it will define the coverage and the approximate amount of time required for it to work and to remove off of surface.

Application

The sprayed coating dries to touch in 10 minutes or less, depending on temperature and film thickness. Application temperature is ambient to no lower than 50°F, as drying times will be affected. Airless sprayer with 1.6 to 1.7mm tip is recommended.

Tack Free Drying time

Boothcoat 5140 will cure tack-free within 60 minutes after application. Curing may be accelerated by forced drying. It is imperative that Boothcoat 5140 be thoroughly cured and dry, with no water being felt before an attempt is made to strip the coating from the substrate

Coverage

Boothcoat 5140 will provide approximately 200 square feet of coverage when applied at 8 mils wet.

Removal

Boothcoat 5140 can be removed by peeling. The dry coating is disposed like paint films and other solid materials

12336 Emerson Dr. | Brighton, MI 48116 | 248-587-5600
Fax: 248-587-5606 | www.gccdatasheets.com