



### TYPICAL PROPERTIES

Appearance: Translucent liquid  
pH: 3.0-4.0  
Viscosity: Comparable to water

# StripPaint 9900

Powder Coat Stripper

## Description

StripPaint 9900 is a paint stripper solution specially formulated for cured coatings. Safe for use on multiple surfaces, including aluminum, zinc, magnesium, brass, stainless steel and steel substrates. Removes powder coating, ecoating, and wet-applied coatings. StripPaint 9900 is designed to be used through multiple bath cycles.

## Recommended Application

1

Use requires an immersion tank.

Ensure there is proper ventilation and that industry standard practices are followed at all times.

2

Immerse parts to be stripped in a solution of 50% StripPaint 9900 and 50% water.

Heat tank to 185F for 20 - 60 minutes.

3

Use pressure washer to rinse parts with clean water.

## Benefits

- Multi purpose- safe on multiple surfaces
- Concentrated for cost effectiveness
- Reduces coating defects

## Health & Safety

Please refer to SDS for complete health and safety information.

## Storage

Keep container closed. Handle and open containers with care. Store in a cool, well ventilated place away from incompatible materials and flame, heat or other source of ignition. Do not reuse empty containers without commercial cleaning. Shelf life is one year from date of manufacture.

## Bath life

It is difficult to predict the length of the bath life because of all the variables involved. They include bath volume, number of parts per cycle, bath maintenance, etc. It is formulated for a long bath life.

## Application

Time is dependent on surface and coating. Parts need to be immersed until coatings are de-laminated. Use polypropylene-evaporation inhibitor-floats to inhibit evaporation. Solution loss should be replenished with 50% StripPaint 9900 and 50% water for optimal stripping performance.

12336 Emerson Dr. | Brighton, MI 48116 | 248-587-5600  
Fax: 248-587-5606 | [www.gccdatasheets.com](http://www.gccdatasheets.com)