

WINDOCOAT 4880

Temporary peelable glass coating



TYPICAL PROPERTIES

Color: blue when wet,
transparent blue when cured
Weight: 8.8 lbs/gallon
Viscosity: Medium to high
Flashpoint: None
pH: 7.5-9
VOC: None
Minimum film forming
temperature > 10°C

SHIPPING

Windocoat 4880 is shipped in 1 gallon metal can, 5 gallon plastic bucket, or 55 gallon open head plastic drum.

Description

Windocoat 4880 provides temporary protection of glass and non-porous window frames or doors during construction from bricklayers, painters, cleaners and anyone else that comes into contact with windows.

WindoCoat 4880 is a water based peelable coating that dries by water evaporation to form a durable water resistant coating that protects windows from damage during the construction phase.

Recommended Application

- 1** Perform patch test.
Ensure surface is clean and free of dirt, oil, and other contaminants.
- 2** Windocoat 4880 should be used as received.
- 3** Apply a minimum of 10 mils of wet film by spray, roller (1/8" nap works best), or camel brush.
- 4** Let cure.
Note: Temperature and humidity will affect dry times.
- 5** Windocoat 4880 can be removed by peeling.
Windocoat 4880 is disposed like paint films and other solid materials.

Benefits

- Excellent outdoor durability
- Excellent water resistance
- Strong and elastic film
- Leaves no residue
- Easy release from variety of substrates
- Cost effective alternative to plastic sheeting

Health & Safety

Please refer to SDS for complete health and safety information.

Storage

Over long standing in storage suggested intermixing prior to application. For best results should be applied at 45°F to 100°F and low humidity. Shelf life is one year from date of manufacture.

Patch Test

Because it is difficult to determine the type of substrate of the window frame, such as type of acrylic, perform a small test first. This will

determine effectiveness, coverage, and the approximate amount of time required for it to work.

Application

Apply at temperatures over 50°F.

Tack Free Drying time

Humidity will effect dry times.

Coverage

When applied to 10 mils thickness, 1 gallon of Windocoat 4880 will provide approximately 160 square feet of coverage.

Removal

Windocoat 4880 should be removed within 12 months of application. It can be removed by peeling. Windocoat 4880 is disposed like paint films and other solid materials.

12336 Emerson Dr. | Brighton, MI 48116 | 248-587-5600
Fax: 248-587-5606 | www.gccdatasheets.com